

October, 2014

3M™ Marine Adhesive Sealant Fast Cure 4200: 06560 • 06564 • 05260

Product Description

A fast curing, one-part polyurethane that chemically reacts with moisture to deliver strong, flexible bonds to wood, gelcoat and fiberglass. It forms watertight, weather-resistant seals on joints and boat hardware above and below the waterline. In addition, its flexibility allows for dissipation of stress caused by shock, vibration, swelling or shrinking.

Product Features

- Fast cure formula
- One component, moisture curing
- Allows for disassembly
- Bonds dissimilar materials
- Extended shelf life
- Adheres to a wide variety of substrates
- Non-sagging
- Permanently elastic



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values
Density	9.75 lb/gal
Consistency	Caulkable, non-sag paste

Typical Mixed Physical Properties

Property	Values		Test Condition
Tack Free Time	1 to 2 h		Room Temperature
Rate of Cure	4 mm per 24 hr	3/16 in per 24 hr	Room Temperature

Typical Cured Characteristics

Shore A Hardness: 40

Methods
ASTM C661

Typical Performance Characteristics

Property	Values		Method
Tensile Strength	1.24 MPa	180 lb/in²	ASTM D412
Elongation at Break	>400 %		ASTM D412
Service Temperature Range	-40 to 88 °C	-40 to 190 °F	

Overlap Shear Strength		Dwell/Cure Time	Substrate	Substrate Notes	Failure mode	Notes	Test Condition
11.6 kg/cm²	165 lb/in²	Room Temperature	Fir	Woods	Cohesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	

Table continued on next page

Typical Performance Characteristics (continued)

Overlap Shear Strength		Dwell/Cure Time	Substrate	Substrate Notes	Failure mode	Notes	Test Condition
7.2 kg/cm ²	100 lb/in ²	Room Temperature	Stainless Steel	Metals	Mixed Cohesive/Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	
7 kg/cm ²	100 lb/in ²	Room Temperature	Aluminum	Metals	Mixed Cohesive/Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	
3.9 kg/cm ²	55 lb/in ²	Room Temperature	Acrylic	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	
6.6 kg/cm ²	95 lb/in ²	Room Temperature	Nylon	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	
7 kg/cm ²	100 lb/in ²	Room Temperature	ABS	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	
2 kg/cm ²	25 lb/in ²	Room Temperature	Polypropylene (PP)	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate. Desirable failure mode is cohesive.	

Table continued on next page

Typical Performance Characteristics (continued)

Overlap Shear Strength		Dwell/Cure Time	Substrate	Substrate Notes	Failure mode	Notes	Test Condition
8.8 kg/cm ²	125 lb/in ²		Cold Rolled Steel	Metals	Mixed Cohesive/Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate.	Room Temperature
7 kg/cm ²	100 lb/in ²		Polycarbonate (PC)	Plastics/Polymers	Mixed Cohesive/Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness) Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate.	Room Temperature
11.6 kg/cm ²	165 lb/in ²		Fiber-Reinforced Plastic	Plastics/Polymers	Cohesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness); Resins used in fiber reinforced plastics often vary. To ensure strong bond, adhesion tests should always be performed on the specific substrates used in application. Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate.	Room Temperature
1.5 kg/cm ²	20 lb/in ²		Low Density Polyethylene (LDPE)	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness); Resins used in fiber reinforced plastics often vary. To ensure strong bond, adhesion tests should always be performed on the specific substrates used in application. Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate.	Room Temperature
5.5 kg/cm ²	75 lb/in ²		PVC	Plastics/Polymers	Adhesive	One inch (2.54 cm) overlap specimens (0.093 inch [0.2362 cm] thickness); Resins used in fiber reinforced plastics often vary. To ensure strong bond, adhesion tests should always be performed on the specific substrates used in application. Cohesive – Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode. Adhesive Failure – Adhesive/Sealant releases from substrate.	Room Temperature

Property: Overlap Shear Strength

Typical Physical Properties**Solids Content by Weight:** 100 %**Handling/Application Information****Directions for Use**

Surface Preparation:

Handling/Application Information (continued)

Abrading the surface with 180- to 200-grit abrasive will enhance the bond strength. Cut the plastic nozzle tip to the desired bead size. Puncture the seal in nozzle end of the cartridge and screw the plastic nozzle in place. Remove the bottom end seal of cartridge and place the cartridge in a caulk gun dispenser. Apply Fast Cure 4200 to the seam or part to be bonded. Position parts and tool material to desired appearance. Tooling of adhesive can be accomplished by using a tongue depressor. If a finger is used, rubber gloves are recommended. Remove excess with General Purpose Adhesive Cleaner 08984 or suitable solvent.

*When using solvents, use in a well ventilated area. Extinguish all sources of ignition in the work area and observe product directions for use and precautionary measures. Refer to product label and MSDS for further precautions. Always pre-test solvent to ensure it is compatible with substrates.

Local and federal air quality regulations may regulate or prohibit the use of these products or surface preparation and cleanup materials. Consult local and federal air quality regulations before using these products.

Note: Alcohol will interfere with the curing process and extra care must be taken when using alcohol as a cleaning solvent to prevent any contact with the sealant.

Primer:

Use of a primer is an extra step and cost and will depend on substrates and the final end use. Using primer can improve the corrosion resistance of certain metals as well as improve the durability of the bond when exposed to high humidity conditions. For most applications, high strength bonds on metal can be achieved without the use of a primer. Pre-testing for adhesion is suggested to determine if a primer is needed. Contact your 3M Technical Service representative for primer recommendation and application advice.

Applications:

3MTM Adhesive Sealant Fast Cure 4200 is designed to allow disassembly of wood and fiberglass parts bonded together. If a permanent bond is desired, use 3MTM Marine Adhesive Sealant 5200 or Marine Adhesive Sealant Fast Cure 5200.

Typical bonding applications include:

- Fiberglass deck to fiberglass hull
- Wood to fiberglass
- Portholes
- Deck fittings
- Moldings
- Trunk joints
- Between struts and planking
- Stern joints

Typical sealing applications include:

- Some plastics (test before assembly)
- Glass
- Metals (priming may be required)

Limitations :

- Alcohol should not be used in preparation for bonding as it will interfere with the curing process, causing the adhesive to fail.
- Due to the decreased value in bond strength at elevated temperatures use of this product is not recommended above 190°F (88°C).
- Do not apply at temperatures below 40°F (4°C) or on frost covered surfaces. Do not apply at surface temperatures above 100°F (38°C).
- Sealant should be used within 24 hours after inner seal is punctured, as product will start to cure in the cartridge and nozzle.
- At 90o F (32o C) and 90% relative humidity, bonds should be made within 15 minutes.
- Some one part solvent-based Marine paints may not cure on top of cured Fast Cure 4200. It is strongly recommended to test all desired paints for suitability.
- Fast Cure 4200 has an elongation much greater than most paints. Most paints will not elongate to this extent before cracking or losing adhesion to the sealant. If the sealant is used in an application where it will elongate or flex to a high degree, it is best not to paint.
- Fast Cure 4200 is not recommended for use as a teak deck seam sealer. Extended exposure to chemicals (teak cleaners, oxalic acid, gasoline, strong solvents and other harsh chemicals) may cause permanent softening of the sealant.
- Fast Cure 4200 is not recommended for the installation of glass, polycarbonate or acrylic windows that are not also mechanically fastened. Inconsistent adhesion of these unprimed substrates, specific design of the window and movement due to thermal expansion and flexing may cause application failure.
- When using 3MTM Marine Adhesive Sealant Fast Cure 4200 with metals it may be necessary to prime the surface to achieve adequate adhesion and durability of the bond. 3M Metal Primer P592 may be used for priming of most metals.

Cleanup:

For cleaning 3MTM Marine Adhesive Sealant Fast Cure 4200 before it is cured, use a dry cloth to remove the majority of sealant, followed by a cloth damp with 3MTM General Purpose Adhesive Cleaner 08984. Cured material can be removed mechanically with a knife, razor blade, piano wire, sanding device.

Storage and Shelf Life

Polyurethane sealants and adhesive sealants must be stored in a controlled environment to maximize shelf life. Store the products in the original unopened containers below 77°F (25C).

When stored at recommended conditions, the shelf life of cartridges and sausage packs is 12 months from the date of manufacture. For 5 and 55 gallon containers, the shelf life is 6 months from date of manufacture.

Trademarks

3M and Scotch-Brite are trademarks of 3M Company.

References

1. 3m.com Product Label Page
Url: https://www.3m.com/3M/en_US/company-us/all-3m-products/~ /3M-Marine-Adhesive-Sealant-Fast-Cure-4200FC?N=5002385+3291170224&rt=rud
2. Safety Data Sheet
Url: https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=4200

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Technical Information

The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer

Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

